

Technical Data

PENGUARD TOPCOAT



Product description

Penguard topcoat is a two pack epoxy topcoat based on polyamide cured epoxy resin. This product is a part of a complete system which is certified not to spread surface flames.

Recommended use

A finish coat in epoxy system. Also on concrete where epoxy paint are specified.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	40	60	50
Film thickness, wet (μm)	80	120	100
Theoretical spreading rate (m^2/l)	12.5	8.33	10

Physical properties

Colour	According to colour card, also can be tinted through Jotun Industrial Multicolor system
Solids (vol %)*	50 \pm 2
Specific Gravity	1.0 – 1.3 (after mixing)
Flash point	25°C \pm 2 (Setaflash)
Gloss	Glossy
Gloss retention	Fair
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Excellent
Chemical resistance	Excellent
Flexibility	Good

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be cleaned with detergent and fresh water.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. When used over concrete / masonry the substrate should not contain more than 4% water (by weight). The coating should not be exposed to water, chemicals or mechanical stress until cured.

Application methods

Spray	Use airless spray
Brush	For smaller areas

Application data

Mixing ratio (volume)	4 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent)
Mixing	½ hour prior to use.
Pot life (23°C)	8 hours. (Reduced at higher temp.)
Thinner/Cleaner	Jotun Thinner No. 17
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² 2100 psi)
Nozzle tip	0.46 - 0.69 mm (0.018-0.027")
Spray angle	40 - 80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	10°C	23°C	35°C
Surface dry	150 min	90 min	30 min
Through dry	14 h	6.5 h	4 h
Cured	14 d	7 d	3 d
Dry to recoat, minimum	14 h	7 h	3 h
Dry to recoat, maximum			

1. Evaluated according to BS 3900 part C2
2. Evaluated according to BS 3900 part C3
3. Recommended data given for recoating with the same generic type of paint
4. Provided the surface is free from chalking and other contamination prior to application, best intercoat adhesion occurs when the subsequent coat is applied before the preceding coat is cured. If this time is exceeding it may be necessary to roughen the surface.

Note: The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Penguard special OR	1 x 80 µm	(Dry Film Thickness)
Penguard Primer	1 x 50 µm	(Dry Film Thickness)
Penguard HB	1 x 100 µm	(Dry Film Thickness)
Penguard Topcoat	1 x 50 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

20 litre unit: 16 litres Comp. A (base) in a 20 litre container and 4 litres Comp. B (curing agent) in a 5 litre container

or

5 litre unit: 4 litres Comp. A (base) in a 5 litre container and 1 litre Comp. B (curing agent) in a 1 litre container

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jeddah - Head Office Jotun Saudia CO. LTD P. O. Box 34698 Jeddah 21478 Saudi Arabia Phone +966 02 6350535 Fax +966 02 6362483	Riyadh - Branch Jotun Saudia CO. LTD P. O. Box 91586 Riyadh 11643 Saudi Arabia Phone +966 01 2430503 Fax +966 01 2709689	Dammam - Branch Jotun Saudia CO. LTD P. O. Box 4906 Dammam 31412 Saudi Arabia Phone +966 03 8473090 Fax +966 03 8474097	Yanbu - Factory Jotun Saudia CO. LTD P. O. Box 30154 Yanbu, Al Sinaiyah Saudi Arabia Phone +966 04 3962911 Fax +966 04 3968483
---	--	---	--

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED MARCH 2005 BY JOTUN SAUDIA CO. LTD
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED
